TECHNICAL DATA SHEET



TDS-1/PR-10

EVODRAIN HARD DN/OD 200-400 mm

DN/OD series R2 type drainage pipe with profiled (corrugated) external and smooth internal surface

DIN 4262-1 EN 13476-3 Material: polypropylene: **(PP)** Ring stiffness: **SN8**

PRODUCT DESCRIPTION

Drainage pipe with profiled (corrugated) external wall and smooth internal surface according to product standard DIN 4262-1 conforms to profile type R2 and perforation classes TP (360° totally perforated drainage pipe), LP (180°±10° or 220°±10° locally perforated pipe), MP (\leq 120° multipurpose pipe) and UP (unperforated liquid transport pipe). Pipes are available in bars - with a pipe length of 6 [m]. Standard set for DN/OD series drainage pipes, with LP, MP and UP perforation class, is equipped with welded-on solid PP coupling and oil resistant sealing ring. The sealing ring is resistant to oil according to the requirements of EN 681-2 p.5.10. The supplied sealing ring grants a hermetic seal with a pressure rating of \geq 0,5 bar (for the coupling area). Pipes are available with a nominal ring stiffness class of SN8.


Outer surface color is black (RAL 9004) but internal surface is white (RAL 9016). Pipe material: PP (polypropylene).

Sealing ring material: EPDM (ethylene-propylene-diene rubber (terpolymer)). Pipe produced according to standard: DIN 4262-1, EN 13476-3.

Sealing rings conform to standard: EN 681-1/A3.



Locally perforated pipe LP(180°±10°)



Multipurpose pipe MP(≤120°)

Ring stiffness: **SN8**

Open product

APPLICATION AREA

Corrugated drainage pipes are best suited for establishing hidden horizontal drainages to ensure dehumidification of the landfills. Drainage is to be installed on the land where ground-water depth is less than dehumidification norm, i.e. where high humidity saturation in the ground may result in slower drying of the productive soil at spring, as well as in destruction of basements of the building, road elution, etc. EVODRAIN HARD R2 type SN8 class drainage pipes are applicable for areas:

- In agriculture, forestry, in parks, squares and peat fields;
- Stadiums and sport complexes;
- Temporary and permanent drainage systems at construction sites;
- Landfills (liquid and biogas collection);
- For civil and industrial buildings and construction areas;
- Airport territory construction;
- Harbour and dock territory construction;
- Road construction application:
 - Without transport load (pavements, pedestrian and bicycle paths);
 - With transport load (railroad, tunnel and highway construction)

Storage of sealing rings according to standards ISO 2230 and EN 681-1/A3 D. Installation performance in accordance with standard EN 1610; CEN/TR 1046.

Updated: 14.11.2025 17:38 Page 1 of 6 PRODUCT PARAMETERS

Durability in low temperature, at $t = -25^{\circ}C$



Website: www.evopipes.lv

TECHNICAL DATA SHEET



TDS-1/PR-10





DN/OD series R2 type drainage pipe with profiled (corrugated) external and smooth internal surface DIN 4262-1 EN 13476-3 Material: polypropylene: (PP) Ring stiffness: SN8

> ISO 1629 ISO 815

ISO 3387



Totally perforated pipe TP(360°)





Material

Pipe physical and mechanical properties				
Parameter	Value	Test method		
Material	PP	DIN 4262-1		
Ring stiffness, kN/m²	8	EN 9969		
Impact resistance 0°C (staircase method)	H ₅₀ ≥1200mm No break below 500 mm	EN 11173		
Sealing ring physical and mechanical properties for LP, MP un UP class pipes				

WCL type rubber sealing ring



Locally perforated pipe LP(220°±10°)



Chemical resistance	pH2 <ph<ph12< td=""><td>ISO/TR 7620</td></ph<ph12<>	ISO/TR 7620	
Permeability pressure	<0,5 bar	EN ISO 13254 EN ISO 13259 Condition B and C	
Oil resistance*	Conforms	EN 681-2	
Pipe flushing (cleaning) allowance parameters			
May prossure bar	120		

EPDM

72 h

168 h


Max pressure, bar 120 80 Minimum flow rate, I/min

*Oil resistant seal acc. to requirements of EN 681-2 p.5.10; conformity determined by Volume change in oil test acc. to ISO 1817



FILTER MATERIAL APPLICATION OPTIONS

Drainage pipes EVODRAIN HARD R2 are produced without filter material overlay. If it is necessary then application of filter material must be done on site. Recommended application of filter material overlay is demonstrated in the tables bellow.



Locally perforated pipe LP(180°±10°)

Class TP 360° totally perforated pipe recommended filter material overlaying options **Option A Option B** Pipe is covered along it's circumference with two identical sheets of filter material overlays

Pipe is covered fully along it's circumference with a single sheet of filter material overlay

5 ÷ 10 cn



Class LP 180°±10° or 220°±10° locally perforated pipes and class MP ≤120° multipurpose pipe recommended filter material overlaying options

Option A Multipurpose pipe MP(≤120°)

Only perforated area is overlaid with a single filter sheet

Pipe is fully covered along it's circumference with a single filter sheet

Option B

Pipe is covered along it's cir-cumference with two identical sheets of filter material overlays

Option C



5 ÷ 10 cm

5 <u>÷ 10 cm</u>

Open product

Ring stiffness: **SN8**

PRODUCT DIMENSIONS

Outside/Inside OD/ID, mm

Perforation opening area, cm²/m

Perforation opening area, cm²/m

Perforation opening area, cm²/m

Perforation opening area, cm²/m

Nominal size

Pipe bar length, m

to profile foot, pcs

to profile foot, pcs

to profile foot, pcs

profile foot, pcs

DN/OD 200-315 mm

Pipe dimensions

Perforation opening parameters for perforation class TP (360°)

Perforation opening parameters for perforation class LP (220°±10°)

Perforation opening parameters for perforation class LP (180°±10°)

Perforation opening parameters for perforation class MP (≤120°)

200/174,6

≥100

3

≥100

2

≥100

2.1



DN/OD 400

400/349,8

6

<u>≥</u>100

6

≥100

2

≥50

4

≥100

1

Website: www.evopipes.lv

TECHNICAL DATA SHEET

Perforation opening quantity on transverse plane normal

Perforation opening quantity on transverse plane normal

Perforation opening quantity on transverse plane normal

Perforation opening ratio on transverse plane normal to



TDS-1/PR-10



DN/OD series R2 type drainage pipe with profiled (corrugated) external and smooth internal surface DIN 4262-1 FN 13476-3 Material: polypropylene: (PP) Ring stiffness: SN8

315/274,1

≥100

3

≥100

2

≥100

2:1

≥50

DN/OD 200 | DN/OD 250 | DN/OD 315

250/215.9

<u>≥</u>100

≥100

2

≥100

2.1

≥50

1



Totally perforated pipe TP(360°)




Locally perforated pipe LP(220°±10°)



Locally perforated pipe LP(180°±10°)






DN/OD 200-400 mm

DN/OD 200-315 mm

LP (220°±10°), locally perforated pipe. Water inlets are located in the upper part of the pipe symmetric to pipes vertical axis in 220°±10° area, but flow line (used for collection and transportation of liquids) is

not perforated and stands opposed to inlet area.

TP (360°), totally perforated pipe. Water inlets are evenly distributed along pipes circumference.



DN/OD 400mm

LP (180°±10°), locally perforated pipe. Water inlets are located in the upper part of the pipe symmetric to pipes vertical axis in 180°±10° area, but flow line (used for collection and transportation of liquids) is not perforated and stands opposed to inlet area.



Open product

DN/OD 200-400 mm

MP (≤120°), multipurpose pipe. Water inlets are located in the upper part of the pipe symmetric to pipes vertical axis in max of 120° area, but flow line (used for collection and transportation of liquids) is not perforated and stands opposed to inlet area.



UP class unperforated liquid transport pipe is used for transportation of water.

STANDARDS APPLICABLE TO PIPES

TDS-1/PR-10

STANDARDS A	PPLICABLE TO PIPES
Standard	Description
DIN 4262-1	Pipes and fittings for subsoil drainage of trafficked areas and underground engineering - Part 1: Pipes, fittings and their joints made from PVC-U, PP and PE
Plastics piping systems for non-pressure underground drainage and sewerage. Structured-wall pipes systems of unplasticized polyvinyl chloride (PVC-U), polypropylene (PP) and polyethylene (PE). Spectrons for pipes and fittings with smooth internal and profiled external surface and the system, Type Pipe geometric parameters according to:	
Pipe mechanical parameters according to:	
EN ISO 9969	Thermoplastics pipes - Determination of ring stiffness
EN 9967	Thermoplastics pipes - Determination of creep ratio
EN 11173	Plastics piping and ducting systems - Thermoplastics pipes - Determination of resistance to external blows by staircase method

APPLICATION BY SUBSTANCE TYPE

Substance type	Without filter material overlay	With A type filter material overlay*	With coco fiber filter material overlay*	
Binding– poorly filtering ground				
Clay	No	No	Yes	
Dense sandstone	No	No	Yes	
Sandstone	No	Yes	Yes	
Non-binding- poorly filtering ground				
Loam	No	Yes	No	
Binding-well filtering ground				
Coarse sand	Yes	Yes	No	
Binding sand	No	Yes	No	
Non-binding sand (loose)	No	Yes	No	
Gravel	Yes	Yes	No	
Turf	No	Yes	Yes	

^{*-} If substance requires a filter material overlay then application of filter overlay must be done on site.


Updated: 14.11.2025 17:38 Page 4 of 6 TDS-1/PR-10



Website: www.evopipes.lv

TECHNICAL DATA SHEET

EVODRAIN HARD R2 SN8 and SN16 pipes application for drainage piping systems



Areas which can only be used by pedestrians and pedal cyclists.

1. Group

Carriageways of roads (including pedestrian streets), hard shoulders and parking areas, for all types of road vehicles.

4. Group

EVODRAIN HARD RF R2, SN16

Areas imposing high wheel loads, e.g. docks, aircraft pavements.

5. Group

EVODRAIN HARD

R2, SN8

EVODRAIN HARD R2,

SN8




Langervaldes iela 2a, Jelgava, Latvia, LV-3002 Phone: e-mail: +371 630-943-00 Info@evopipes.lv



Website: www.evopipes.lv

TECHNICAL DATA SHEET



Vw - terrestrial water; **Lw** - infiltration water;

Kw - capillary water; **Sw** - water layer;

Dw - groundwater, still water

Is 1 - inside traffic load influence area (from 1 track)

Is 2 - inside traffic load influence area (from 2 tracks)

As - outside traffic load influence area

Ss - traffic load influence area


Ais - area outside of traffic load influence

Drainage pipe nominal ring stiffness class (SN) selection by usage area and ground group				
	Ais	As	ls 1 and ls 2	
	EVODRAIN HARD R2 type SN8	EVODRAIN HARD R2 type SN8	EVODRAIN HARD RF R2 type SN16	
	Applicable to all ground groups*	Applicable to all ground groups*	Applicable to G1, G2 and G3 ground groups*	

*Ground groups according to ATV-A 127

G1 - non-binding sand and gravel G2 - well binding sand and gravel G3 - binding mixed ground and coarse sand G4 - binding ground (e.g. clay)

AIRPORT TERRITORY APPLICATION



ID: TDS-1.V2EN-EVODRAIN.HARD.SN8.OD_200-400

Updated: 14.11.2025 17:38 Page 6 of 6